Application No.: 10/588,062

AMENDMENTS TO THE CLAIMS:

Please amend the claims as follows:

1. (Currently amended) An alkaline battery comprising: a negative electrode including

an electrode mixture that contains a zinc or zinc alloy powder as an active material; an alkaline

electrolyte; and a positive electrode,

wherein said zinc or zinc alloy powder has a specific surface area of 0.01 to 10 m²/g, and

the weight ratio of said electrolyte the alkaline electrolyte contained in the battery to the active

material (electrolyte/negative electrode active material) is in the range of 0.1 to 2, and

said electrode mixture contains 0.15 to 0.9 wt% of lithium hydroxide.

2. (Cancelled)

3. (Currently Amended) The alkaline battery in accordance with claim 1, wherein said

zinc or zinc alloy powder has a specific surface area of 0.1 to 5 m²/g, and the weight ratio of said

electrolyte the alkaline electrolyte contained in the battery to the active material is in the range of

0.2 to 0.7.

2